

SYG-780 WHITE ASSEMBLY PASTE

Product Description

Mounting paste for lubricating sliding points at which dark lubricants are not desired and where frictional corrosion is to be avoided for optimum adhesion, clean contamination and other lubricants from sliding surfaces. Best way is to clean mechanically first (for example, with a wire brush) and then with good cleaner. Apply the paste evenly and thinly with a brush, spatula, etc.

Remove excesses. Do not use paste instead of grease and mix only with suitable lubricants

Applications

- Assembly lubrication of sliding points
- Screw lubrication at normal temperatures and low speeds
- Lubrication when joining parts

Benefits

- Prevents frictional corrosion on joint connections of steel parts of all kinds subject to vibration loading under damp-room and aggressive operating conditions
- Low consumption thanks to thin-film lubrication
- Excellent water resistance
- Excellent lubricating and separating effect
- Good corrosion protection behavior
- Metal-free

Typical Properties

SYG-780	Specifications
base oil	white oil
solid lubricants	white solid lubricants with PTFE
thickener	Hydro oxysterate lithium soap
color	light-colored
density (at 20°C), g/cm ³ , DIN EN ISO 3838	1.25
flashing point, °C, DIN ISO 2592	200
Drop point din iso 2176	200
four-ball test rig welding load, N, DIN 51350-4	5000
lower operating temperature, °C	-25
press-fit test, μ, draft DIN 51 833	0.09, no chatter
thread friction coefficient (μ), DIN EN ISO 16 047	0.08
thread friction coefficient (μ), DIN EN ISO 16 047	0.08
unworked penetration, 0.1 mm, DIN ISO 2137	250-280
upper operating temperature, °C	150
viscosity at (40°C), mm ² /s, DIN 51 562-1	100
water resistance, Degree 0-3, DIN 51 807-1	0-90

Available Packs: 18 and 180 Kg.

Shelf Life – 36 Months from the Manufacturing month.

* All related specifications are meets or exceeds.

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly. The Material Safety Data Sheet (MSDS) are available upon request through our sales office.

1. PRODUCT AND COMPANY IDENTIFICATION

Product SYG-780 WHITE ASSEMBLY PASTE
Supplier PETRELPLUS INC.

One World Center, Tower One, 9th Floor, Senapati Bapat Marg, Lower Parel, Mumbai-400013, Maharashtra.
Call # +91 22 6216 7072
(Monday to Friday)
Cell # +91 93522 25457
marketing@petrelplus.com
www.petrelplus.com

2. COMPOSITION

No Reportable Hazardous Substance(s) or Complex Substance(s). Composition of Base oil, thickener and performance- based additives.

3. HAZARDS IDENTIFICATION

Not classified as Hazardous.

4. FIRST-AID MEASURES

RESPIRATORY SYSTEM: Remove to fresh air and get medical attention.

INGESTION: Do not induce vomiting. Wash mouth out with water and obtain medical attention.

EYES: Rinse immediately with plenty of water for at least 10 minutes. Get Medical Attention.

SKIN: Remove contaminated clothing. Wash affected area with soap and water, get medical attention.

5. FIRE-FIGHTING METHODS

Foam, carbon dioxide or dry powder.

6. ACCIDENTAL RELEASE MEASURE

Contain and absorb in sand or earth. Ensure no material enters drains or water courses. Dispose of as solid waste in accordance with the relevant waste disposal regulations.

7. STORAGE AND HANDLING

Handling - At ambient temperatures wear gloves overalls and eye protection. The work area should be adequately ventilated. No eating drinking or smoking in the work area.
Storage - Store in delivery packs in a cool & dry place.

8. EXPOSURE CONTROL / PERSONAL PROTECTION

Exposure Standard:

The substance with exposure limit is: Notation 1: Exposure Standard: 2nd substance with exposure limit is: Notation 2:

PERSONAL PROTECTION

Respiratory Protection:

Type of Cartridge (if Applicable): Eye Protection: Safety Spectacles

Hand Protection: Gloves butyl or nitrile rubber

Industrial Hygiene: No eating drinking or smoking in the work area Ventilation: At room temperature handle in a well-ventilated area.

Use exhaust ventilation if exposure to flume or aerosol can occur.

PROTECTION AGAINST FIRE AND EXPLOSION

Combustible but not readily ignited. No explosion hazard.

EC SAFETY PHRASES: Not classified as hazardous.

9. TYPICAL PROPERTIES

Color - Light
Drop point, °C - 200
Solid Lubricant - Present
Thickener - Lithium Soap

10. STABILITY AND REACTIVITY

HAZARDOUS REACTIONS

Comments

HAZARDOUS DECOMPOSITION PRODUCTS Thermal decomposition produces noxious fumes.

11. TOXICOLOGICAL INFORMATION

LD50 Acute Oral Toxicity: > 5000:mg/Kg:Rat

LC50 Acute Inhalation: :mg/1

Eye Irritation: No: Rabbit

Skin Irritation: No.: Rabbit

Sensation: No

Further Information:

12. ECOLOGICAL INFORMATION

LC50 (96 Hour): mg/1

EC50 (24 Hour): mg/1

Biodegradability (Coupled units):

13. DISPOSAL CONSIDERATIONS

Solid material should be incinerated. Material absorbed on sand should be disposed of as solid waste.

14. TRANSPORT INFORMATION

IMDG No.: Not classified

Packing Groups: IATA-DGR Class No.: Not classified

TREMCARD: Not classified

RID/ADR Class No.: Not classified

Other Information

15. REGULATORY INFORMATION

Classification and labeling according to EC Directives 67/548

Not classified as hazardous. EC Risk Phrases

Not classified as hazardous. Other Hazardous

EC Safety Phrases

Not classified as hazardous

16. OTHER INFORMATION: PRODUCT SAFETY

For safety reasons, it is IMPERATIVE that customer: - Ensure that all those within their control who use the products are supplied with all relevant information contained within the Material Safety Data Sheet and Technical Bulletin concerning the applications for which the product is designed and any instructions or warning.

DISCLAIMER/USER'S RESPONSIBILITY: PETRELPLUS INC. Provides the information contained herein in good faith but makes no representation as to its comprehensiveness or accuracy. This document is intended only as a guide to the appropriate precautionary handling of the material by a properly trained person using this product. Individuals receiving the information must exercise their independent judgment in determining its appropriate use.